

Portable Amperometric Glucose Detection based on NiS/CuS Nanorods Integrated with a Smartphone Device

Heyu Zhao¹, Kaige Qu¹, Haoyong Yin^{1*}, Ling Wang², Yifan Zheng³, Shumin Zhao¹, and Shengji Wu^{4*}

¹Wenzhou Institute of Hangzhou Dianzi University, Wenzhou, 325038, China

²Department of Chemistry, Zhejiang Sci-Tech University, Hangzhou, 310018, P. R. China

³Research Center of Analysis and Measurement, Zhejiang University of Technology, Hangzhou 310014, P. R. China

⁴College of Engineering, Huzhou University, 313000, Huzhou, China

Table S1. The parameters of the equivalent circuit elements derived from the EIS measurements

Electrodes	R _s (Ω)	R _{ct} (Ω)	W (Ω)	C (F)
NiS/CuS	40.79	7.74	1.31×10 ²	1.99×10 ⁻⁶
NiO/CuO	39.66	14.21	2.09×10 ³	2.42×10 ⁻⁷

*E-mail address: yhy@hdu.edu.cn (Haoyong Yin), wushengji26@hdu.edu.cn (Shengji Wu)

DOI: <https://doi.org/10.33961/jecst.2023.00073>

This is an open-access article distributed under the terms of the Creative Commons Attribution Non-Commercial License (<http://creativecommons.org/licenses/by-nc/4.0>) which permits unrestricted non-commercial use, distribution, and reproduction in any medium, provided the original work is properly cited.